Atty. Docket No.: 2003B101A Amdt. dated June 3, 2009

Reply to OA of March 5, 2009

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in this application.

Listing of Claims:

- 1.-22. (Cancelled)
- 23. (Currently Amended) A film comprising an A/B/A structure, wherein: core layer B comprises 60-90 wt.% LDPE and 40-10 wt.% HDPE, and skin layers A are each independently selected from a composition comprising:
 - (a) 80-100 85-95 wt.% mLLDPE; and
 - (b) 5 -15 wt.% of HDPE, LDPE, or a mixture thereof, 20 0 wt.% HDPE, and 20 0 wt.% LDPE.
- 24. (Currently Amended) A film comprising an A/B/A structure, wherein: the A layers are skin layers, which may be the same or different, each comprising:
 - (a) an mPE prepared from ethylene and at least one C₃ to C₁₂ alpha-olefin monomer and having a density of between about 0.910 g/cm³ to about 0.940 g/cm³; and
 - (b) <u>HDPE</u>, <u>LDPE</u>, or both, said <u>HDPE</u> having a density of between 0.940 and <u>0.970 g/cm³</u>, and
 - the B layer is a core layer comprising a blend comprising 60-90 wt.% LDPE and 40-10 wt.% HDPE.
- 25. (Cancelled)
- 26. (Previously Presented) The film according to claim 23, wherein said mLLDPE has a density of between 0.915 to 0.940 g/cm³.

Atty. Docket No.: 2003B101A

Amdt. dated June 3, 2009 Reply to OA of March 5, 2009

Reply to Off of March 3, 2003

27. (Previously Presented) The film according to claim 23, wherein the HDPE in said B

layer has a density of between 0.940 and 0.970 g/cm³.

28. (Previously Presented) The film according to claim 23, wherein said LDPE has a

density of between about 0.916 to 0.935 g/cm³.

29. (Previously Presented) The film according to claim 23, wherein said layers A and

layer B, when formed into a coextruded structure A/B/A having a total thickness of

less than 50 microns, has a 1% secant Modulus MD of at least 400 mPa, and a 1%

secant Modulus TD of at least 400 mPa, both measured in accordance with ASTM

D882.

30. (Previously Presented) The film according to claim 29, wherein the 1% secant

Modulus MD is at least 500 mPa, and the 1% secant Modulus TD is at least 500 mPa,

measured in accordance with ASTM D882.

31. (Currently Amended) The film according to claim 23, wherein the core layer B

comprises 70-80 wt.% LDPE and 30-20 wt.% HDPE, and the skin layers A are each

independently selected from a blend comprising 85-95 wt.% mPE mLLDPE and 15-5

wt.% HDPE LDPE.

32. (Previously Presented) The film according to claim 23, wherein each of said layers A

and layer B have a total thickness of less than 50 microns, a difference in Gloss 20°

and 60° of 2% or less, where the Gloss values are measured in accordance with

ASTM D2457.

33. (Previously Presented) The film according to claim 23, further comprising at least

one layer between at least one of said A/B layers, said at least one layer selected from

the group consisting of a tie layer, a reprocessed material layer, and a layer selected

from blends comprising an HDPE and an LDPE.

Atty. Docket No.: 2003B101A

Amdt. dated June 3, 2009

Reply to OA of March 5, 2009

34. (Previously Presented) A coextruded, heat-shrinkable film according to claim 23.

35. (Previously Presented) A collation shrink-wrapped structure comprising a group of

items wrapped by means of a film according to claim 23.

36. (Previously Presented) A process for making a packaged structure, comprising

wrapping a package with the film according to claim 23, and heating the wrapped

package to shrink the film and apply a holding force to the structure.

37. (Previously Presented) The film according to claim 24, wherein at least one of said A

layers comprises HDPE and LDPE, said LDPE present in an amount of from 2 to 10

wt%, said HDPE having a density of between 0.960 to 0.965 g/cm³.

38. (Previously Presented) The film according to claim 23, wherein said LDPE has a

density of between 0.925 to 0.935 g/cm³.

39. (Previously Presented) The film according to claim 24, wherein said mPE is an

mLLDPE having a density of from about 0.918 to about 0.927 g/cm³.

40. (Previously Presented) The film according to claim 39, wherein at least one of said A

layers further comprises an HDPE having a density of from about 0.940 to about

 0.970 g/cm^3 .

41. (Previously Presented) The film according to claim 39, wherein the HDPE in said B

layer has a density of from about 0.940 to about 0.970 g/cm³.

42. (Previously Presented) The film according to claim 39, wherein said LDPE has a

density of from about 0.916 to about 0.935 g/cm³.

Atty. Docket No.: 2003B101A

Amdt. dated June 3, 2009 Reply to OA of March 5, 2009

reply to off of March 2, 2005

43. (Currently Amended) The film according to claim 39, wherein the core layer B

comprises 70-80 wt.% LDPE and 30-20 wt.% HDPE, and the skin layers A are each

independently selected from a blend comprising 85-95 wt.% mPE and 15-5 wt.%

HDPE LDPE.

44. (Previously Presented) The film according to claim 39, wherein the layers A and

layer B, when formed into a coextruded structure A/B/A having a total thickness of

less than 50 microns, has a 1% secant Modulus MD of at least 400 MPa, and a 1%

secant Modulus TD of at least 400 MPa, both measured in accordance with ASTM

D882.

45. (Previously Presented) The film according to claim 44, wherein the coextruded

structure A/B/A has a 1% secant Modulus TD of at least 600 MPa, measured in

accordance with ASTM D882.

46. (Previously Presented) The film according to claim 39, wherein said layers A and

layer B, when formed into a coextruded structure A/B/A having a total thickness of

less than 50 microns, has a difference in Gloss 20° and 60° of 2% or less, the Gloss

values measured in accordance with ASTM D2457.

47. (Previously Presented) The film according to claim 39, further comprising at least

one layer between at least one of said A/B layers, said at least one layer selected from

the group consisting of a tie layer, a reprocessed material layer, and a layer selected

from blends comprising an HDPE and an LDPE.

48. (Previously Presented) A coextruded, heat shrinkable film according to Claim 39.

49. (Previously Presented) A collation shrink-wrapped structure comprising a group of

items wrapped by means of a film according to Claim 39.

Atty. Docket No.: 2003B101A Amdt. dated June 3, 2009 Reply to OA of March 5, 2009

50. (Previously Presented) The film of claim 23, wherein the mLLDPE is prepared from ethylene and at least one C_3 to C_{12} alpha-olefin monomer.

- 51. (Currently Amended) The film of claims 23 and or 24, wherein slip or antiblock additives are excluded from the skin layer.
- 52. (Currently Amended) The film of claims 23 and or 24, wherein slip or antiblock additives are excluded from the skin and core layers.